

	Symbol	Unit	Measuring Conditions			Conventional Low Loss Material P41
			Freq.	Flux den.	Temp.	
Initial Permeability	μ_i		$\leq 10\text{kHz}$	0.25mT	25°C	2400 $\pm$ 25%
Amplitude Permeability	μ_a		25kHz	200mT	25°C	> 4500
					100°C	> 4500
Power Loss	Pv	KW/m ³	25kHz	200mT	25°C	125
					100°C	50
			100kHz	200mT	25°C	650
					100°C	350
			300kHz	100mT	25°C	820
					100°C	500
			500kHz	50mT	25°C	400
					100°C	300
Saturation Flux Density	Bs	mT	10kHz	H = 1200A/m	25°C	495
					100°C	395
Remanence	Br	mT	10kHz	H = 1200A/m	25°C	170
					100°C	55
Coercivity	Hc	A/m	10kHz	H = 1200A/m	25°C	13
					100°C	6
Hysteresis Material Constant	η_B	10 ⁻⁶ /mT	10kHz	1.5-3.0mT	25°C	< 1
Disaccommodation Factor	Df	10 ⁻⁶	10kHz	< 0.25 mT	25°C	< 2
Curie Temperature	Tc	°C				≥ 230
Resistivity	ρ	Ωm				4.00
Density	d	g/cm ³				4.85

Note: Material characteristics are typical for a toroid core.

Product specification will differ from these data due to the influence of geometry and size.

