

	Symbol	Unit	Measuring Conditions			High Frequency Low Loss Material
			Freq.	Flux den.	Temp.	P5
Initial Permeability	μ_i		$\leq 10\text{kHz}$	0.25mT	25°C	2000 $\pm$ 25%
Amplitude Permeability	μ_a		25kHz	200mT	25°C	> 4000
					100°C	> 4000
Power Loss	Pv	KW/m ³	300kHz	100mT	25°C	600
					100°C	350
			500kHz	50mT	25°C	220
					100°C	250
			700kHz	50mT	25°C	600
					100°C	550
Saturation Flux Density	Bs	mT	10kHz	H = 1200A/m	25°C	470
Remanence	Br	mT	10kHz	H = 1200A/m	25°C	135
					100°C	70
Coercivity	Hc	A/m	10kHz	H = 1200A/m	25°C	17
					100°C	10
Hysteresis Material Constant	η_B	10 ⁻⁶ /mT	10kHz	1.5-3.0mT	25°C	< 1
Disaccommodation Factor	Df	10 ⁻⁶	10kHz	< 0.25 mT	25°C	< 2
Curie Temperature	Tc	°C				≥ 220
Resistivity	ρ	Ωm				6.40
Density	d	g/cm ³				4.70

Note: Material characteristics are typical for a toroid core.

Product specification will differ from these data due to the influence of geometry and size.

